

Stain-Resistant White Spray Lacquer for Plastics

Formulation No: C1 – 5

Ingredients	w/w
Elvacite® 2010	6.04
Xylene	14.60
Methyl Ethyl Ketone	9.53
"Bakelite" VYHH Vinyl Chloride-Acetate Resin	6.04
Methyl Ethyl Ketone	47.31
"Aromatic" 100 Solvent	1.88
n-butyl acetate	6.84
Dibutyl Sebacate	1.08
"Bentone" 34	0.94
"Ti-Pure" R-900	<u>5.74</u>
	100.00
PVC	15.3%
Solids % ^w / _w	19.8
% ^v / _v	11.4

Typical viscosity #4 Fordcup, sec = 13

Preparation:

Dissolve Elvacite 2010 in a mixture of Xylene with the indicated portion of MEK. Dissolve vinyl resin in remaining solvents and combine with Elvacite solution. Add plasticiser (n-butyl sebacate), Bentone and pigment and disperse.

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users should make their own tests to determine the suitability of these products for their own particular purposes. Lucite International Inc. MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to its applicable current Standard Specifications. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Lucite International Inc, for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products or formulations described herein are not to be construed as recommending the infringement of any patent, and Lucite International Inc, assumes no liability for infringement arising out of such use.