

### High Gloss Metal Top Coat

*Formulation No: D2 – 10, Status Code B*

Ingredients		w/w
Elvacite® 2016	} blend	29.18
Xylene		35.02
Solvesso 100		8.75
Disperbyk		0.21
Rheotix 240		0.50
Tioxide TR92		17.49
Butyl Benzyl Phthalate		1.27
Xylene		6.06
Solvesso 100		<u>1.52</u>
		100.0

Closed cup flash point = 24 °C

**USA** Lucite International, Inc. • 7275 Goodlett Farms Parkway • Cordova TN 38016  
(800) 458-2483 • WWW.LUCITEINTERNATIONAL.COM

**EUROPE** Lucite International Speciality Polymers & Resins Ltd • Horndale Ave • Newton Aycliffe • Co. Durham DL5 6YE UK  
TEL: + 44 (0) 1325 300990 • FAX: + 44 (0) 1325 314925 • WWW.LUCITEINTERNATIONAL.COM

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users should make their own tests to determine the suitability of these products for their own particular purposes. Lucite International MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to its applicable current Standard Specifications. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Lucite International, for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products or formulations described herein are not to be construed as recommending the infringement of any patent, and Lucite International, assumes no liability for infringement arising out of such use.