

SOYGOLD[®]

FORMULARY

COATING REMOVER – CR1

SoyGold 1000 or SoyClear 1500	50.00%
Propylene Carbonate	25.00%
Dibasic Ester	25.00%
Dye	---

Mix Instructions:

1. Add SoyGold or SoyClear, Propylene Carbonate, and Dibasic Ester and mix until homogenous.
2. Add Dye in desired.

This formulation is a suggested starting point for the development of optimized formulations for the individual's specific application.

CONFIDENTIAL

Ag ENVIRONMENTAL PRODUCTS L.L.C.
Corporate Headquarters 1-800-247-1345
12700 West Dodge Road Omaha, NE 68103-2047
www.soygold.com