

Metallic High Gloss Refinish Coating

Formulation No: D1 – 14, Status Code C

Ingredient	w/w	Supplier
Xylene	25.0	Lucite International
PM acetate	10.0	
Butanol	5.0	
Elvacite® 2008	30.0	
Butyl benzyl phthalate	6.0	
Mar Agent	0.3	Siberline
Sparkle Silver 3000AR (65% nv)	3.7	
MIBK	<u>20.0</u>	
	100.0	

The formulation can be easily diluted to spray viscosity. Sparkle Silver 3000AR is used for car repair coatings to resist atmospheric attack (acid rain, sulphur dioxide).

This formulation can also be used as a chemical resistant plastic coating for PS (polystyrene), ABS (acrylonitrile-butadiene-styrene), PMMA (Perspex) and PVC (polyvinyl chloride) with good hardness and durability.

USA Lucite International Inc. • 7275 Goodlett Farms Parkway • Cordova TN 38016
(800) 458-2483 • WWW.LUCITEINTERNATIONAL.COM

EUROPE Lucite International Speciality Polymers & Resins Ltd • Horndale Ave • Newton Aycliffe • Co. Durham DL5 6YE UK
TEL: + 44 (0) 1325 300990 • FAX: + 44 (0) 1325 314925 • WWW.LUCITEINTERNATIONAL.COM

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users should make their own tests to determine the suitability of these products for their own particular purposes. Lucite International MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to its applicable current Standard Specifications. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Lucite International, for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products or formulations described herein are not to be construed as recommending the infringement of any patent, and Lucite International, assumes no liability for infringement arising out of such use.