

### White Lacquer for Plastics

#### *Formulation No: C2 - 4*

Ingredients	w/w
Elvacite® 2014	6.0
Ethyl Acetate	9.8
Isobutyl Acetate	14.0
Propylene Glycol Monoethyl Etheracetate	10.0
½ sec Butyrate	6.0
Sucrose Acetate Isobutyrate	3.0
"Ti-Pure" R-960	5.0
Toluene	<u>46.2</u>
	100.0

PVC		8.9%
Solids	% w/w	20.0
	% v/v	13.4

#### *Preparation:*

Dissolve ½ sec butyrate and sucrose acetate isobutyrate in ester solvents and combine with Elvacite® dissolved in Toluene. Add pigment and disperse.

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users should make their own tests to determine the suitability of these products for their own particular purposes. Lucite International Inc. MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to its applicable current Standard Specifications. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Lucite International Inc, for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products or formulations described herein are not to be construed as recommending the infringement of any patent, and Lucite International Inc, assumes no liability for infringement arising out of such use.

ELVACITE® is a registered trademark of Lucite International Inc.