

Concrete Sealer Formulation

Formulation No: F2 – 3, Status Code B

Ingredients	w/ w
Elvacite® 2016	16.43
Xylene	24.66
MPA 60X	1.69
Methanol	0.32
Bentone 38	1.06
Soya Lecithin	0.11
Tioxide TR92	4.52
Xylene	<u>51.21</u>
	100.00

Closed cup flash-point = 27°C

For Further Information Contact:

USA

Lucite International
Lucite Center
7275 Goodlett Farms Parkway
Cordova TN 38016
TEL: 800 4-LUCITE
www.luciteinternational.com

Europe

Lucite International Speciality Polymers & Resins Ltd.
Horndale Ave - Newton Aycliffe Co.
Newton Aycliffe Co.
Durham DL5 6YE UK
TEL: +44 (0) 1325 300990
FAX: +44 (0) 1325 314925
www.luciteinternational.com

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users should make their own tests to determine the suitability of these products for their own particular purposes. Lucite International, Inc. MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to its applicable current Standard Specifications. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Lucite International, for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products or formulations described herein are not to be construed as recommending the infringement of any patent, and Lucite International, assumes no liability for infringement arising out of such use.

ELVACITE® is a registered trademark of Lucite International, Inc.