

COATING REMOVER - CR3

SoyGold 1000 or SoyClear 1500 50.00%

N-Methyl Pyrolidone (NMP) 25.00%

Tetrahydrofurfuryl Alcohol (THFA) 25.00%

Dye ---

Mix Instructions:

- 1. Add SoyGold or SoyClear, NMP, and THFA and mix until homogenous.
- 2. Add Dye in desired.

This formulation is a suggested starting point for the development of optimized formulations for the individual's specific application.

CONFIDENTIAL

Ag ENVIRONMENTAL PRODUCTS L.L.C.
Corporate Headquarters 1-800-247-1345
12700 West Dodge Road Omaha, NE 68103-2047
www.soygold.com