

Starting Formulation for PVC Topcoat

Formulation No: C1 – 27, Status Code C

Ingredients	w/w	
Elvacite® 2021 or 2010	5.0	(2021 gives slightly tougher coating)
PVC/PVAc resin	6.0	
CAB	0.5	
Dibutyl phthalate	3.5	
MEK	30.0	
MIBK	30.0	
THF	<u>25.0</u>	
	100.0	

USA Lucite International, Inc. • 7275 Goodlett Farms Parkway • Cordova TN 38016
(800) 458-2483 • WWW.LUCITEINTERNATIONAL.COM

EUROPE Lucite International Speciality Polymers & Resins Ltd • Horndale Ave • Newton Aycliffe • Co. Durham DL5 6YE UK
TEL: + 44 (0) 1325 300990 • FAX: + 44 (0) 1325 314925 • WWW.LUCITEINTERNATIONAL.COM

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users should make their own tests to determine the suitability of these products for their own particular purposes. Lucite International MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to its applicable current Standard Specifications. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Lucite International, for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products or formulations described herein are not to be construed as recommending the infringement of any patent, and Lucite International, assumes no liability for infringement arising out of such use.