



# Rust Preventative-Good Quality Long Term

WT %
75.0 SoyGold 1000
25.0 Actrasol SS (Climax Chemical)

### **Blending Procedure:**

Mix ingredients in order listed with vigorous agitation.

Appearance: Crystal clear amber liquid

The information given in this formulary is, to the best of our knowledge, accurate. The formulations are intended to be helpful, but no warranty is expressed or implied regarding the accuracy of the data. It is the user's responsibility to determine the suitability of his use of the products described herein, and since the conditions of use are out of our control, we disclaim all liability with respect to the use of any materials supplied by Ag Environmental. Nothing contained herein shall be construed as permission or as a recommendation to practice any patented invention without a license from the patent owner nor as a recommendation to use any product or to practice any process in violation of any law or any government regulations.



# Rust Preventative-Economy Short Term

WT %

LO.O SoyGold 1000

15.0 Lonzest PEG-4-0 (Lonza Chemical)


25.0 Petronate L (Witco)

### **Blending Procedure:**

Mix ingredients in order listed with vigorous agitation.

Appearance: Crystal clear amber liquid

The information given in this formulary is, to the best of our knowledge, accurate. The formulations are intended to be helpful, but no warranty is expressed or implied regarding the accuracy of the data. It is the user's responsibility to determine the suitability of his use of the products described herein, and since the conditions of use are out of our control, we disclaim all liability with respect to the use of any materials supplied by Ag Environmental. Nothing contained herein shall be construed as permission or as a recommendation to practice any patented invention without a license from the patent owner nor as a recommendation to use any product or to practice any process in violation of any law or any government regulations.



# Rust Preventative-Premium Long Term

WT %

50-0 SoyGold 1000

30.0 Actrasol SR-75 (Climax Chemical)

15.0 Calcium Stearate (Witco)

5.0 Emerest 2302 (Witco)

## **Blending Procedure:**

Mix ingredients in order listed with vigorous agitation.

Appearance: Crystal clear amber liquid

The information given in this formulary is, to the best of our knowledge, accurate. The formulations are intended to be helpful, but no warranty is expressed or implied regarding the accuracy of the data. It is the user's responsibility to determine the suitability of his use of the products described herein, and since the conditions of use are out of our control, we disclaim all liability with respect to the use of any materials supplied by Ag Environmental. Nothing contained herein shall be construed as permission or as a recommendation to practice any patented invention without a license from the patent owner nor as a recommendation to use any product or to practice any process in violation of any law or any government regulations.



# Rust Remover-Acid Type

WT % &L.O SoyGold LOOO 15.O Phosphoric Acid &5% 4.O Igepal CO-530 (Rhodia)

### **Blending Procedure:**

Mix ingredients in order listed with vigorous agitation.

Appearance: Crystal clear amber liquid

The information given in this formulary is, to the best of our knowledge, accurate. The formulations are intended to be helpful, but no warranty is expressed or implied regarding the accuracy of the data. It is the user's responsibility to determine the suitability of his use of the products described herein, and since the conditions of use are out of our control, we disclaim all liability with respect to the use of any materials supplied by Ag Environmental. Nothing contained herein shall be construed as permission or as a recommendation to practice any patented invention without a license from the patent owner nor as a recommendation to use any product or to practice any process in violation of any law or any government regulations.