

Tint Base Metal Lacquer for Outdoor Exposure

Formulation No: D2 – 5, Status Code A

Ingredients	w/w
Elvacite® 2013	10.54
Methyl Ethyl Ketone	71.28
Methyl Amyl Ketone	8.39
"Santiciser" 160	2.10
"Ti-Pure" R-960	<u>7.69</u>
	100.00

PVC	15%
Solids % w/w	20.3
% v/v	11.7

Preparation:

Dissolve Elvacite® 2013 into solvents, add plasticiser and pigment, and disperse. Tint as desired by adding dry colour(s) in the mill or Colour dispersion(s) after milling.

USA Lucite International Inc. • 7275 Goodlett Farms Parkway • Cordova TN 38016
(800) 458-2483 • WWW.LUCITEINTERNATIONAL.COM

EUROPE Lucite International Speciality Polymers & Resins Ltd • Horndale Ave • Newton Aycliffe • Co. Durham DL5 6YE UK
TEL: + 44 (0) 1325 300990 • FAX: + 44 (0) 1325 314925 • WWW.LUCITEINTERNATIONAL.COM

The information and recommendations in this publication are, to the best of our knowledge, reliable. Users should make their own tests to determine the suitability of these products for their own particular purposes. Lucite International MAKES NO WARRANTY OF ANY KIND, EXPRESSED OR IMPLIED, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, other than that the material conforms to its applicable current Standard Specifications. Statements herein, therefore, should not be construed as representations or warranties. The responsibility of Lucite International, for claims arising out of breach of warranty, negligence, strict liability or otherwise is limited to the purchase price of the material. Statements concerning the use of the products or formulations described herein are not to be construed as recommending the infringement of any patent, and Lucite International, assumes no liability for infringement arising out of such use.