



## Furniture Polish

WT %

75.0 Water

18.0 SoyGold 1000

4.0 Witconol 14 (Witco)

2.0 Silicone Fluid 350 cs

1.0 Shell Sol 71 (Odorless Mineral Spirits)

q.s. Fragrance

### Blending Procedure:

1. Combine Water and Witconol 14 in main mixing vessel.
2. In a separate vessel, combine SoyGold 1000, Silicone Fluid and OMS.
3. With agitation, slowly begin to add the oil phase to the main mix vessel and mix until uniform.

The information given in this formulary is to the best of our knowledge accurate. The formulations are intended to be helpful, but no warranty is expressed or implied regarding the accuracy of the data. It is the users responsibility to determine the suitability of his use of the products described herein, and since the conditions of use are out of our control, we disclaim all liability with respect to the use of any materials supplied by AEP. Nothing contained herein shall be construed as permission or as a recommendation to practice any patented invention without a license from the patent owner nor as a recommendation to use any product or to practice any process in violation of any law or any government regulations.