

## CASTOR OIL-FREE LIPSTICK with COLORONA® CHAMELEON (PL-4-92A)

INCI NAME	TRADE NAME/MANUFACTURER	%
<b>Phase A</b>		
<i>Euphorbia Cerifa</i> (Candelilla) Wax	Candelilla Wax, Cosmetic Grade/ Strahl & Pitsch	6.50
<i>Copernicia Cerifa</i> (Carnauba) Wax	Carnauba Wax #1/ Strahl & Pitsch	2.00
Ozokerite	Ozokerite Wax #77W/Ross	6.50
Lauryl Laurate	Purester 24/Strahl & Pitsch	4.00
Cocoglycerides	Myritol 331/Cognis	11.10
Methyl Soyate	Soy Gold 1000/AG Environmental	11.00
Ethylhexyl Hydroxystearate	Schercemol OHS/Scher	21.00
Triisononanoiln	Isodragol/Dragoco	8.00
Octyldodecyl Stearoyl Stearate	Pelemol ODSS/Phoenix Chemical	7.00
Octyl Dodecanol	Eutanol G/Cognis	5.00
<i>Butyrospermum Parkii</i> (Shea Butter) Fruit	Shea Butter/Desert Whale	2.50
<b>Allantoin</b>	<b>Allantoin/Rona</b>	<b>0.20</b>
<b>Phyllanthus emblica Fruit Extract</b>	<b>Emblica™/RONA</b>	<b>0.10</b>
Propylparaben	Propylparaben/Spectrum Chemical	0.10
<b>Phase B</b>		
<b>Iron Oxides (and) Mica</b>	<b>Colorona® Chameleon/Rona</b>	<b>15.00</b>
<b>Total</b>		<b>100.00</b>

**Procedure:** Combine Phase A. Heat to 80-85°C with Lightnin' mixer agitation, stirring until clear. Add Phase B, maintaining agitation until dispersed. Pour into pre-heated molds at 72-74°C.

The information given and the recommendations made herein are based on our research and are believed to be accurate but no guarantee of their accuracy is made. This information is intended to be helpful, but no warranty is expressed or implied as to the results obtained from use of the formulation, procedure or products suggested herein. Neither is any permission or recommendation to practice any invention covered by patent either expressed or implied.

Rona PL-4-92A 2-02