



ETHOCEL™

Ethyl Cellulose Polymers for
Industrial Applications

iff

Where science
& creativity meet

WHAT ARE ETHOCEL™ ETHYL CELLULOSE POLYMERS?

ETHOCEL™ Ethyl Cellulose (EC) Polymers are cellulose ethers that are derived from natural wood or other cellulosic materials. To obtain ETHOCEL™, wood pulp is treated with sodium hydroxide to form alkali cellulose, which is then treated with ethyl chloride to form ethyl cellulose.



IFF IS A WORLD LEADER IN CELLULOSIC DERIVATIVES

ETHOCEL™ EC Polymers offer specific properties that are unique compared to other cellulose ethers. Most cellulose ethers, such as carboxymethyl cellulose or hydroxypropyl methylcellulose, are water-soluble. ETHOCEL™ EC Polymers are not water-soluble, making them an excellent choice for protecting materials and products against water.

IFF invented ETHOCEL™ EC Polymers and has continued to pioneer them for over 80 years. Like other cellulosic polymers in IFF's portfolio, ETHOCEL™ can be fine-tuned to create customized solutions. ETHOCEL™ is backed by IFF's world-class Research & Development team, regional Technical Application teams and regional laboratories. ETHOCEL™ EC Polymers are manufactured in our Michigan Operations plant in Midland, Michigan, USA.

A RANGE OF FUNCTIONAL PROPERTIES

- Organo solubility
- Binder
- Forms clear and resistant films
- Water barrier
- Thermoplasticity
- Viscosity (4 to 300 mPas in 5% solution)
- Rheology modification
- High purity: combusts without residue
- Low toxicity
- No ionic charge
- Enzymatic resistance

UNIQUE PROPERTIES DEVELOPED FOR YOUR APPLICATION NEEDS

Naturally-derived cellulose ether, making it a good choice for consumer applications, such as food contact packaging.

Low Toxicity

Film Former

Forms clear and resistant films. Improves spreadability, suspension and homogeneity in paints, coatings and inks.

Extensive product and molecular weight options enable users to customize the required viscosity and rheology according to their applications.

Viscosity & Rheology Modification

Binding

Exhibits superior binding capabilities and is used in many electronic applications where binding, high purity and film-forming properties are required.

Useful property in various applications across a wide range of industries, particularly in specialty packaging.


Water Barrier

Organo Soluble

Soluble in many organic solvents. (Solvent solubility indicated on Page 6).

Low Ash Content


ETHOCEL™ has a very low ash content, providing high purity and clean burn out for high-end electronic applications.



ETHOCEL™ EC APPLICATIONS

ETHOCEL™ is a versatile polymer, soluble in many organic solvents.

Though it can be used in a wide variety of applications, below are a few select examples.



Used in coatings, paints and inks formulations because of ideal binding, rheology modification and stabilization properties. ETHOCEL™ is a good alternative to other polymers made from nonrenewable sources.

Coatings, Inks

Photovoltaics

Widely used in photovoltaics applications because of binding properties in silver or aluminum electrode pastes.

Used as a seed coating polymer and in crop treatment products with oily actives to stabilize emulsions.

Agriculture

Displays

The premier binder for plasma display panels (PDPs).

Electronics

ETHOCEL™ is the world-premier binder for multi-layer ceramic capacitors (MLCC) and other high-end electronic ceramic parts. It provides clean burn-out, high purity, high solubility, thixotropy for print and adhesion for lamination.

OUR LARGE PRODUCT LINE OPTIMIZES YOUR APPLICATION PERFORMANCE

This product table highlights the key grades in our ETHOCEL™ family. Other product options are available depending on your specific application requirements.

PRODUCT	Viscosity (mPa*s)	Ethoxyl Content (Weight %)	Industrial Applications
ETHOCEL™ Standard 4	3.0 – 5.5	48.0 – 49.5%	Conductive pastes Printing inks Specialty coatings
ETHOCEL™ Standard 7	6.0 – 8.0	48.0 – 49.5%	Conductive pastes Printing inks Specialty coatings
ETHOCEL™ Standard 10	9.0 – 11.0	48.0 – 49.5%	Ceramics Conductive pastes Printing inks Specialty coatings
ETHOCEL™ Standard 20	18.0 – 22.0	48.0 – 49.5%	Specialty coatings Printing inks
ETHOCEL™ Standard 45	41.0 – 49.0	48.0 – 49.5%	Ceramics Conductive pastes Printing inks Specialty coatings
ETHOCEL™ Standard 100	90 – 110	48.0 – 49.5%	Ceramics Conductive pastes Low solid coatings Specialty coatings
ETHOCEL™ Standard 200	180 – 220	48.0 – 49.5%	Conductive pastes Low solid coatings Specialty coatings
ETHOCEL™ Standard 300	270 – 330	48.0 – 49.5%	Conductive pastes Low solid coatings
ETHOCEL™ Medium 70	63.0 – 77.0	45.0 – 47.0%	Conductive pastes Optical films

* All viscosity test solutions are prepared with 5% ETHOCEL™ and measured in an Ubbelohde viscometer at 25°C:

- for Standard products, solvent is a 80% toluene and 20% ethanol combination
- for Medium products, solvent is a 60% toluene and 40% ethanol combination

Please contact an IFF sales representative to discuss product options.

PROCESSING RECOMMENDATIONS FOR ETHOCEL™

ETHOCEL™ solubility


The table below does not list concentrations or viscosities and is only intended as a general guide for the solubility of ETHOCEL™ Standard grades. In general, ETHOCEL™ polymers are most soluble in blends of aromatic hydrocarbons and aliphatic alcohols.

Completely Soluble	Moderately Soluble	Insoluble
Clear Solutions	Hazy Solutions / Swollen Gels	No Interaction
Aromatic Hydrocarbons	Acetates	Aliphatic Hydrocarbons
Chlorinated Hydrocarbons	Esters	Mineral Spirits
Monohydric Alcohols	Alkyl Ethers	Glycols
Glycol Ethers	Naphtha	Glycerol
Ketones	Turpentine	Water



GLOBAL SPECIALTY SOLUTIONS

- Global manufacturing and technology footprint
- Robust business continuity planning



WHAT WE DO

ETHOCEL™ EC Polymers for industrial applications are available only from IFF and its distributors. IFF's Global Specialty Solutions business, manufactures cellulosic polymers alongside other IFF portfolio products. Our dedicated team of experts commercializes these products into various global markets.

WHO WE ARE

We are innovative problem solvers, drawing on deep application understanding and market insight to help our customers turn challenges into high-value business opportunities.



Connect with us

For more information connect with IFF sales and application experts

iff.com

Product Safety

When considering the use of any IFF products in a particular application, please review our latest Material Safety Data Sheets first to ensure that your intended use can be accomplished safely. For Material Safety Data Sheets and other product safety information, contact IFF at the provided numbers. Before handling any other products mentioned in the text, obtain available product safety information and take necessary steps to ensure safety of use.

IFF hereby expressly disclaims (i) any and all liability in connection with such information, including, but not limited to, any liability relating to the accuracy, completeness, or usefulness of such information, and (ii) any and all representations or warranties, express or implied, with respect to such information, or any part thereof, including all representations and warranties of title, noninfringement of copyright or patent rights of others, merchantability, fitness or suitability for any purpose, and warranties arising by law, statute, usage of trade or course of dealing.

The information provided herein is based on data IFF believes, to the best of its knowledge, reliable and applies only to the specific material designated herein as sold by IFF. The information contained herein does not apply to use of the material designated herein in any process or in combination with any other material and is provided at the request of and without charge to our customers. Accordingly, IFF cannot guarantee or warrant such information and assumes no liability for its use. Other than as may be expressly set forth in a contract of sale, IFF makes no warranty, express or implied, as to the material set forth herein, including the warranty of merchantability or fitness for a particular use. ©2023 International Flavors & Fragrances Inc. (IFF). IFF, the IFF Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by IFF or affiliates of IFF unless otherwise noted. All rights reserved.

